

**Technical data sheet**

011121MBA

**Cored welding wire****ROBOFIL B CrMo2****CLASSIFICATION**

ASME IIC SFA 5.29 / AWS A 5.29	E91T5-B3 H4
EN ISO 17634-A	T CrMo2 B M21 3 H5
ASME IX Qualification	QW-432 F-N° 6 QW-442 A-N° 4

**DESCRIPTION**

- Seamless copper coated tubular wire for gas shielded flux cored arc welding
- Single and multiple pass welding of creep resisting steels alloyed with 2.25Cr-1Mo
- Optimal productivity by combining advantages of both seamless and seamed tubular wires
- $H_{DM}$  guaranteed < 4 ml/ 100g deposited metal over the whole parameter box
- No moisture pick up, excellent wire feeding properties, good weldability and low spatter
- Designed for service temperatures up to 550°C

**APPLICATIONS**

Welding creep-resisting steels of similar composition.  
Preheat at 150-250°C and stress relief at 660 -700°C must be carried out.

**Examples**

Creep resisting steel	EN 10028-2	10 CrMo 9-10
	EN 10222-2	12 CrMo 9-10
	ASTM A387gr .21 & 22, A182F22, A217WC9, A234WP22	
	ASTM A199, A200T3b, T4, T21, T22, A213T22	
	ISO/TR 15608: Group 5.2	

**TYPICAL ALL-WELD METAL ANALYSIS**

C	Mn	Si	Cr	Mo
0.06	0.8	0.3	2.3	1

**MINIMUM ALL-WELD METAL PROPERTIES**

	Rm [MPa]	Rp0.2% [MPa]	A <sub>5</sub> [%]	CVN [J]
P.W.H.T 1h / 690°C	620	540	18	+ 20°C: 47

**TYPICAL ALL-WELD METAL PROPERTIES**

	Rm [MPa]	Rp0.2% [MPa]	A <sub>5</sub> [%]	CVN [J]
P.W.H.T 1h / 690°C	650	560	22	+ 20°C: 120

**SHIELDING GAS**

ISO 14175: M20 (Ar + 5 - ≤ 15% CO<sub>2</sub>), M21 (Ar + 15 - 25% CO<sub>2</sub>)

**OPERATING CONDITIONS**

Diameter [mm]	Current type	Current [A]	Voltage [V]	Stick-out [mm]
1.2	DC+ or pulsed	100 - 350	16 - 34	12 - 25
1.6	DC+ or pulsed	160 - 470	20 - 36	15 - 25

**WELDING POSITIONS**

ROBOFIL B CrMo2 is primarily used in the flat and horizontal-vertical positions. However, welds in other positions are also possible using the short-circuiting or pulsed arc modes of transfer.

**PACKAGING**

Diameter	1.2 mm	1.6 mm
	EN ISO 544 – ASME IIC SFA-5.2 M	
Spool type	BS300	
Weight	15 kg	

Other packaging and other diameters: please consult us

Welding products and techniques evolve constantly. All descriptions, illustrations and properties given in this data sheet are subject to change without notice and can only be considered as suitable for general guidance. This document is intended to help the user make the correct choice of product. It is his responsibility to assess its suitability for his intended application.