

HARDFACE LP-G

For Welding Professionals



**The ideal hardfacing solution
for out of position jobs**



HARDFACE LP-G is an out of position flux cored wire for gas shielded arc hardfacing. It is suited to fight moderate abrasion and is resistant to impact and metal-to-metal wear.

The wire produces a medium alloyed welding deposit and can be used on parts such as bucket lips, crusher jaws, crusher hammers, cutting tools, to name a few.


Extend the service life of parts and reduce total cost of ownership by protecting them with HARDFACE LP-G.

Why choose this solution?

- Fast freezing slag
- Outstanding slag release
- Applicable in multiple layers (2-3) without cracks
- Self tempering deposit
- High deposition rate compared to standard 600HB solid wire (+20-25%)



Product Details

Classification:	EN 14700: T Fe8
Available Diameter:	1.2 mm and 1.6 mm
Hardness:	55 HRC (as welded, one-layer deposit)
Welding Positions:	



contactus@welding-alloys.com
www.welding-alloys.com

