

Technical data sheet

011121MBA

**Cored welding wire
HARDFACE 38-S****CLASSIFICATION**

EN 14700: T Fe1

DESCRIPTION

- Tubular wire for submerged arc hardfacing
- Hardfacing or rebuilding parts by depositing an alloy with chemical composition close to that of 18CD4 and 15CDV6

APPLICATIONS

- Rebuilding continuous casting rollers or rolling cylinders

TYPICAL ALL-WELD METAL ANALYSIS

C	Mn	Si	Cr	Mo
0.10	1.00	0.40	1.50	0.50

Structure: bainite

TYPICAL ALL-WELD METAL MECHANICAL PROPERTIES

Hardness - 3-layer deposit - As welded: 230 – 280 HB

FLUX DESCRIPTION

	WA FLUX 325	WA FLUX 385	WA FLUX 415	WA ULTRAFLUX
EN ISO 14174 class	S A AB 1 65	S A AF 2 64	S A FB 1 55	S A FB 1 55

OPERATING CONDITIONS

Diameter [mm]	Current [A]		Voltage [V]		Stick-out [mm]	
	Range	Optimum	Range	Optimum	Range	Optimum
2.4	200 - 450	350	26 - 30	30	25 - 60	30
2.8	250 - 550	400	28 - 32	30	25 - 60	30
3.2	300 - 650	500	28 - 32	30	25 - 60	30

Recovery : 95 %

Current type/polarity: DC+ or DC-

WELDING POSITIONS

EN ISO 6947: PA, PB.

ASME IX: 1G, 1F, 2F

PACKAGING

Diameter	≥ 2.4 mm	
Standard packaging	B 450 coil	Drum
Weight	25 kg	Up to 330 kg

Other packaging and other diameters: please consult us