


<b>Technical data sheet</b>  EN131223GB	<b>Cored welding wire</b>  <b>CHROMECORE V 410NiMo-G</b>	
---	--	---

### CLASSIFICATION

EN ISO 17633-A	T 13 4 P M21 1
ASME IIC SFA 5.22	E410NiMoT1-4
EN 14700	T Fe7
Equivalent material number	1.4351

### DESCRIPTION

- Flux cored wire with fast freezing rutile-basic slag for gas shielded arc welding of stainless steels
- Specifically designed for out-of-position welding, maximum productivity for completion of vertical welds
- 12% Cr - 4% Ni – 0.5% Mo soft martensitic stainless steel
- Welded with classical economical Ar-CO<sub>2</sub> mixtures or CO<sub>2</sub>
- Diffusible hydrogen guaranteed below 4 ml per 100 g of weld metal (typically around 3 ml/100g)

### APPLICATIONS

CHROMECORE V 410NiMo-G is used for the fabrication and rebuilding of turbines in the hydropower industry. The deposit is martensitic and combines good toughness with excellent resistance to cavitation and to stress corrosion cracking. Together with enhanced productivity, especially for vertical welding, the CHROMECORE V 410NiMo-G offers many other advantages compared to solid wires: improved weldability, almost no spatter, better arc stability, enhanced wetting properties, reduced crack sensitivity, better bead appearance and shape.

#### Examples of materials to be welded (non exhaustive list):

- EN Symbol: X4 CrNi 13 4, X3 CrNiMo 13 4, X3 CrNi 13-4, GX4 CrNiMo 13-4, GX5 CrNi 13 4, GX5 CrNiMo 13-4
- Material number: 1.4313, 1.4407, 1.4413, 1.4414
- UNS: S41500, J91540, J91550
- Wrought: F6NM, Cast CA6NM, ASTM A352, A487, A743, A757

A post-weld heat treatment at 580°C - 620°C is recommended to obtain a tempered martensite that combines strength and ductility with corrosion and cavitation resistance.

### TYPICAL ALL-WELD METAL ANALYSIS

C	Mn	Si	Cr	Ni	Mo
0.03	0.4	0.3	12.0	4.5	0.5

### MINIMUM ALL-WELD METAL MECHANICAL PROPERTIES

	Rm [MPa]	Rp0.2%[MPa]	A <sub>5</sub> [%]	CVN [J]	
PWHT 8 hours at 580°C	760	500	15	+20°C : 45	-20°C : 40

### TYPICAL ALL-WELD METAL MECHANICAL PROPERTIES

	Rm [MPa]	Rp0.2%[MPa]	A <sub>5</sub> [%]	CVN [J]	
PWHT 8 hours at 580°C	830	690	18	+20°C : 50	-20°C : 45

Recovery: 90%

### OPERATING CONDITIONS – PF / 3G up

Diameter [mm]	Current type	Intensity [A]	Voltage [V]	Stick-out [mm]
1.6	DC+	130 - 230	20 - 26	10 - 20

### SHIELDING GAS

EN ISO 14175: M21 (Ar + 15 - 25% CO<sub>2</sub>)  
M20 (Ar + 5% < CO<sub>2</sub> < 15%)

### WELDING POSITIONS

EN ISO 6947: PA, PB, PC, PD, PE, PF, PG  
ASME IX: 1F, 1G, 2F, 2G, 3F, 3G, 4F, 4G, 5G

### PACKAGING

Diameter	1.6 mm
Spool type (EN ISO 544)	BS 300
Weight	15 kg

Other packaging: please consult us

Welding products and techniques evolve constantly. All descriptions, illustrations and properties given in this data sheet are subject to change without notice and can only be considered as suitable for general guidance. This document is intended to help the user make the correct choice of product. It is his responsibility to assess its suitability for his intended application.